

# Non Woven Specifications

## 8 oz. Non Woven Geotextile Fabric

### SPECIFICATIONS

Property	Test Method	Roll Value
Tensile Strength	ASTM-D-4632	205 lbs.
Elongation	ASTM-D-4632	50%
Trapezoidal Tear	ASTM-D-4533	85 lbs.
CBR Puncture Strength	ASTM-D-6241	535 lbs.
AOS	ASTM-D-4751	80 Sieve
Permittivity	ASTM-D-4491	1.35 Sec-1
Water Flow Rate	ASTM-D-4491	90 gpm/ft.
UV Resistance	ASTM-D-4355	70% / 500 hours

Unless otherwise noted, this certification is based on testing conducted by our Quality Assurance & Quality Control testing laboratories at the time of manufacturing. Erosion Control Products offers this letter of certification to indicate our commitment to providing our customers with a quality product which will meet or exceed minimum average roll values in accordance with the applicable American Society for Testing and Materials (ASTM) test method.

For more complete information on our products and solutions, visit us on the Web at [www.erosioncontrol-products.com](http://www.erosioncontrol-products.com)

Phone: 1-863-563-3357 | [info@supplysourceusa.com](mailto:info@supplysourceusa.com)  
© 2021 ECP. All rights reserved. Terms and conditions apply.

All photos are representative only. Actual products may differ. Materials and specifications are subject to change without notice. Featured products in photos may include additional equipment or accessories.